



Extraction Thimbles, specifications

Grade	Material	Retention* liquid µm	Wall Thickness mm	Weight gram per 25x90 mm thimble	Pressure Drop kPa /5 liter/min.	Retention Efficiency % 0,3 µm DOP	Max. Temperature °C	Heating Loss Rate %
610	Cellulose	8	1.5	-	-	-	120	-
84	Cellulose	8	1.5	3.6	0.25	89	120	-
86R	Glass Fibers	1	1.6	1.6	0.30	>99.9	500	0.2
88R	Quartz Fibers	3	1.6	2.2	0.44	>99.9	1000	-
88RH	Quartz Fibers	3	1.6	2.2	0.44	>99.9	1000	0.1
89	PTFE	1.5	1.8	11.0	4.5	>99.9	260	-
89S	PTFE/Quartz	-	1.6	6	0.54	>99.9	400	0.7

* nominal